

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
25 May 2001 (25.05.2001)

PCT

(10) International Publication Number
WO 01/36535 A1

(51) International Patent Classification⁷: C08L 75/04, 23/10

(21) International Application Number: PCT/US00/31279

(22) International Filing Date:
14 November 2000 (14.11.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/166,229 18 November 1999 (18.11.1999) US

(71) Applicant: THE DOW CHEMICAL COMPANY
[US/US]; 2030 Dow Center, Midland, MI 48674 (US).

(72) Inventors: FARAH, Hani; 2702 Field Line Drive, Sugarland, TX 77479 (US). LERMA, Francisco, Jr.; 6509 Acorn Court, Pearland, TX 77581 (US).

(74) Agent: WILLIS, Reid, S.; Intellectual Property, P.O. Box 1967, Midland, MI 48641-1967 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

- With international search report.
- Before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments.

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: COMPATIBILIZED RESIN BLENDS AND THE PREPARATION THEREOF

(57) Abstract: The present invention is a blend of a polymeric hydrocarbon and a thermoplastic polyurethane which is a compatibilized polymeric hydrocarbon that contains low concentrations of isocyanate reactive group. The compatibilizer can be prepared by reacting a modified polymer having pendant or incorporated amine-reactive groups with a hydroxyl amine, a diamine, or a polyethermonoamine. The compatibilized blend may further include a non-TPU engineering thermoplastic to form compatible blends of the polymeric hydrocarbon and the non-TPU engineering thermoplastic. In this case, the TPU is used as a co-compatibilizer.

WO 01/36535 A1

COMPATIBILIZED RESIN BLENDS AND THE PREPARATION THEREOF

This invention relates to compatibilized resin blends of normally incompatible polymers and the preparation of such blends.

Compatibilizers for blends of certain polymers are known in the art. For example, U.S. Patent 5,959,032 (Evans et al.) describes the preparation of a compatibilizer (for polypropylene and a thermoplastic polyolefin) which is the reaction product of an anhydride functionalized polypropylene and a polyetheramine.

JP Patent Application No. 3-231963 discloses a blend of a thermoplastic polyurethane and a polyolefin that is compatibilized with a polyolefin modified with carboxyl groups, anhydride groups, and/or epoxy groups. The compatibilized blend is reported to have high heat-resistance, high mechanical strength, and high wear resistance.

The compatibilized blends of the prior art generally suffer from having undesirably low weldline strength, which is important for applications such as automotive instrument panels or bumper beams, the manufacture of which generally requires multiple gate or complex injection molding design. Accordingly, it would be desirable to have available a compatibilizer that addresses this deficiency.

The present invention is a composition comprising a blend or reactive product of a) a thermoplastic polyurethane, and b) a compatibilizer, which is a first polymeric hydrocarbon that contains isocyanate-reactive groups or polyoxyalkylene groups.

In a second aspect, the present invention is a composition comprising a blend or reactive mixture of a) a thermoplastic polyurethane, and b) a compatibilizer, which is a first polymeric hydrocarbon that contains isocyanate reactive groups or polyoxyalkylene groups, and c) a second polymeric hydrocarbon, wherein the first and second polymeric hydrocarbons are each independently selected from the group consisting of polypropylene, high density polyethylene, low density polyethylene, linear low density polyethylene, substantially linear ethylene/ α -olefin copolymers, polystyrene, poly- α -methylstyrene, polyvinyltoluene, and ethylene-styrene interpolymers.

In a third aspect, the present invention is a method of preparing a compatibilizing composition comprising the step of compounding under reactive conditions a) a thermoplastic polyurethane, and b) a compatibilizer, which is a first polymeric hydrocarbon that contains isocyanate reactive groups.

In a first aspect the present invention is a composition comprising a blend or reactive product of a) a thermoplastic polyurethane, and b) a compatibilizer. The compatibilizer, which is a first polymeric hydrocarbon containing either isocyanate reactive groups or polyoxyalkylene groups, is advantageously prepared by contacting under reactive conditions a) a first polymeric hydrocarbon having pendant or incorporated amine-reactive groups with either b) a compound that contains at least one amine group and at least one isocyanate-reactive group; or c) a compound that contains an amine group and polyoxyalkylene group.

As used herein, the term polymeric hydrocarbon refers to a polyolefin, a polymer of an alkenyl aromatic hydrocarbon, or a polymer prepared from olefinic and alkenyl aromatic hydrocarbon monomers. The term isocyanate-reactive group refers to a group that reacts with an isocyanate group, preferably an amino group or hydroxyl group.

Examples of polyolefins include polypropylene, high density polyethylene (HDPE), low density polyethylene (LDPE), linear low density polyethylene (LLDPE), or substantially linear ethylene/ α -olefin copolymers such as those copolymers described in U.S. Patents 5,272,236 and 5,278,272. Examples of polymers of alkenyl aromatic hydrocarbons include polymers of styrene, α -methylstyrene, and vinyltoluene. An example of a polymer prepared from olefinic and alkenyl aromatic hydrocarbon monomers is ethylene-styrene interpolymers.


Amine-reactive groups can be made pendant to the backbone of the first polymeric hydrocarbon by grafting an ethylenically unsaturated amine-reactive compound onto the backbone of the polymeric hydrocarbon. Alternatively, amine-reactive groups can be incorporated into the backbone of the polymeric hydrocarbon by copolymerization of the olefin or alkenyl aromatic hydrocarbon monomer or both with an ethylenically unsaturated amine-reactive compound. Grafting is a preferred means of incorporating the amine-reactive groups into the polymeric hydrocarbon.

As used herein, the term "ethylenically unsaturated amine-reactive compound" refers to a compound that a) can be attached to the polymeric hydrocarbon by grafting or copolymerization and b) is chemically reactive with an amine. Similarly, the term "amine-reactive group" is used herein to refer to the remnant formed by grafting or copolymerization. Examples of ethylenically unsaturated amine-reactive compounds that can be grafted onto the polymeric hydrocarbon backbone or copolymerized with the olefin or alkenyl aromatic hydrocarbon monomer include ethylenically unsaturated carboxylic acids such as maleic acid, fumaric acid, itaconic acid, acrylic acid, methacrylic acid, and crotonic acid; acid anhydrides such as maleic anhydride and itaconic anhydride; vinyl benzyl halides such as vinyl benzyl chloride and vinyl benzyl bromide; alkyl acrylates and methacrylates such as methyl acrylate, ethyl acrylate, butyl acrylate, lauryl acrylate,

5 methyl methacrylate, ethyl methacrylate, butyl methacrylate, and lauryl methacrylate; and ethylenically unsaturated oxiranes such as glycidyl acrylate, glycidyl methacrylate, and glycidyl ethacrylate. Preferred ethylenically unsaturated amine-reactive compounds include maleic anhydride, acrylic acid, methacrylic acid, glycidyl acrylate, glycidyl methacrylate, with maleic anhydride being more preferred. Polypropylene grafted with maleic anhydride is a more preferred modified polymeric hydrocarbon. An example of a commercially available modified polymeric hydrocarbon is EPOLENE™ PP 3003 wax (a trademark of Eastman Chemical Co), which is a propylene wax that contains from about 0.5 to 1 weight percent grafted maleic anhydride units.

10 The degree of incorporation or grafting of the amine-reactive group is application dependent, but is preferably not more than 10 weight percent, more preferably not more than 5 weight percent, more preferably not more than 2 weight percent, and most preferably not more than 1 weight percent; and preferably not less than 0.01 weight percent, more preferably not less than 0.1 weight percent, and most preferably not less than 0.2 weight percent, based on the weight of the compatibilizer.


15 The hydroxylamine is a compound containing an amine group and at least one hydroxyl group, preferably only one hydroxyl group. The amine can be a primary or a secondary amine, and is preferably a primary amine. The polyamine is a compound that contains at least two amine groups, preferably only two amine groups. An example of a suitable class of hydroxylamines or polyamines is represented by the following formula:



where X is O or NH, where each R is independently H, -CH₃, or -CH₂CH₃; and where x is from 0 to 50. The disclosure and preparation of hydroxyl amines can be found in US Patents 3,231,619, 4,612,335, and 4,888,446, which teachings are incorporated herein by reference. Examples of preferred oxyalkanolamines include 2-aminoethanol, 1-amino-2-propanol, 2-amino-1-propanol, 3-amino-1-propanol, 2-(2-aminoethoxy)ethanol, 1-amino-2-butanol, 2-amino-3-butanol, and polyoxyalkylene glycol amines. 2-Aminoethanol is a preferred alkanolamine.


30 The polyamine is a compound with at least two amine groups. Examples of suitable polyamines include α-ω alkylene diamines such as ethylene diamine, 1,3-propylene diamine, 1,4-butylene diamine, and 1,6-hexylene diamine, as well as polyoxyalkylene diamines, commercially available as JEFFAMINE™ polyoxyalkylene diamines (a trademark of Huntsman Petrochemical). Where the amine-reactive groups pendant to the backbone of the first polymeric hydrocarbon are

maleic anhydride groups, the compatibilizer prepared using polyamines or alkanolamines contains pendant groups characterized by the following structure:



where X is NH or O, each R is independently H, -CH₃, or -CH₂CH₃; and where x is from 0 to 50.

- 5 Polyoxyalkylene groups can be incorporated into the backbone of the first polymeric hydrocarbon by reacting the amine-reactive groups with a polyether monoamine such as described by Evans et al. in U.S. Patent 5,959,032, and commercially available as JEFFAMINE™ M-1000 and JEFFAMINE™ 2005 resins (a trademark of Huntsman Chemical). A compatibilizer prepared using polyether monoamines preferably contains pendant groups characterized by the following structure:
- 10



where R₁ C₁-C₄ alkyl, each R is independently H, -CH₃, or -CH₂CH₃; and where x is from 0 to 50.

A stoichiometric excess of the hydroxylamine, polyamine, or polyether monoamine is used so as to ensure complete or substantially complete conversion of the amine-reactive groups.


- 15 The thermoplastic polyurethane (TPU) can be an engineering thermoplastic polyurethane or ETPU (also known as a rigid TPU) or a soft TPU. ETPUs have a glass transition temperature (T_g) of greater than 50° C and contain less than 25 weight percent of units of a high molecular weight diol (that is, a diol having a molecular weight of not less than 500 amu). Preferably, the units of the high molecular weight diol constitute not more than 10 weight percent of the ETPU,
- 20 more preferably not more than 5 weight percent of the ETPU, and more preferably not more than 1 weight percent of the ETPU. A most preferred ETPU contains 0 units of the high molecular weight diol.

Examples of commercially available ETPUs include ISOPLAST™ resins (a trademark of The Dow Chemical Company), the preparation of which is disclosed, for example, by Goldwasser

et al. in U.S. Patent 4,376,834 and by Oriani in U.S. Patent 5,627,254, which teachings are incorporated herein by reference. The ETPU contains structural units of a chain extender such as 1,6-hexanediol or a blend of 1,4-butanediol and a polyethylene glycol. Preferably the chain extender is a blend of 1,4-butanediol and a polyethylene glycol, more preferably 1,4-butanediol and diethylene glycol or triethylene glycol, and most preferably 1,4-butanediol and triethylene glycol.

The TPU may also be a soft TPU having a T_g of less than 25° C and a Shore A hardness of not more than 95. An example of a commercially available soft TPU is PELLETHANE™ thermoplastic polyurethane resin. (PELLETHANE is a trademark of The Dow Chemical Company.)

The TPU may be blended or reacted with the compatibilizer. For example, if the compatibilizer contains isocyanate-reactive groups, the blend can be compounded under heat and shear to cause the TPU, particularly the ETPU, to depolymerize to form isocyanate groups and hydroxyl groups. Upon cooling, the isocyanate groups can react with the isocyanate-reactive groups of the compatibilizer to form new urethane linkages. For example, where the compatibilizer is prepared by the reaction of polypropylene grafted with maleic anhydride and 2-aminoethanol or ethylene diamine, the reaction product of the compatibilizer and the ETPU is presumed to have the following structural attribute:



where X is NH or O. Alternatively, if the compatibilizer contains polyoxyalkylene groups that do not react with isocyanate, then the TPU is believed not to react with the compatibilizer.

In a second aspect, the present invention is a composition comprising a blend or reactive mixture of a) the TPU, b) the compatibilizer, and c) a second polymeric hydrocarbon. The composition is preferably either a compatibilized dispersion of the TPU in the second polymeric hydrocarbon matrix, or a dispersion of the second polymeric hydrocarbon in the polyurethane matrix. For a compatibilized dispersion of a TPU in the second polymeric hydrocarbon, the

concentration of the TPU, preferably the ETPU is from about 10 to about 40 weight percent, based on the weight of the TPU, the second polymeric hydrocarbon, and the compatibilizer. For a compatibilized dispersion of the second polymeric hydrocarbon in the TPU, preferably the ETPU, the concentration of the second polymeric hydrocarbon in the TPU, is preferably not less than 5 weight percent, and not more than 40, more preferably not more than 30, and most preferably not more than 20 weight percent, based on the weight of the TPU, the second polymeric hydrocarbon, and the compatibilizer.

The amount of compatibilizer used is application dependent, but in general is used at a level sufficient to increase the unnotched izod impact at the weldline or the tensile strength as compared to a second polymeric hydrocarbon and thermoplastic polyurethane blend that contains no compatibilizer. Preferably, the amount of compatibilizer is not less than about 0.5 weight percent, more preferably not less than 1 weight percent, and most preferably not less than 2 weight percent; and preferably not more than 20 weight percent, more preferably not more than 15 weight percent, and most preferably not more than 10 weight percent, based on the total weight of the second polymeric hydrocarbon, the TPU, and the compatibilizer.

The compatibilizer of the present invention can also be used to form a dispersion of the second polymeric hydrocarbon and a broad range of engineering thermoplastics other than TPU (hereinafter, the second engineering thermoplastic), provided the blend contains a co-compatibilizing amount of a TPU. Examples of other engineering thermoplastics include polyesters such as polyethylene terephthalate (PET) and polybutylene terephthalate (PBT), polycarbonates such as Bisphenol-A-polycarbonate, polyamides such as nylons, polyoxymethylenes such as polyacetals, polysulfones, polyarylates, polyarylene oxides such as polyphenylene oxide (PPO), polyvinyl alcohol, polyvinyl acetate, and ethylene-vinyl acetate copolymer, ethylene-vinyl alcohol copolymer, and polyether lactones.

As used herein, a "co-compatibilizing amount" refers to the amount of TPU required to increase the weldline strength or percent elongation of a composition that contains the second polymeric hydrocarbon, the second engineering thermoplastic, and the compatibilizer as compared to a composition that does not contain the TPU. Preferably, the weight-to-weight ratio of the compatibilizer to the TPU is not less than 1:10, more preferably not less than 1:5, and most preferably not less than 1:2; and preferably not greater than 10:1, more preferably not greater than 5:1, and most preferably not greater than 2:1. When TPU is used as a co-compatibilizer, it is preferably used at a level of not less than 0.1 weight percent, more preferably not less than 1 percent, and most preferably not less than 2 weight percent; and preferably not more than 20 weight percent, and more preferably not more than 10 weight percent, based on the weight of the polymeric hydrocarbon, the second engineering thermoplastic, the TPU, and the compatibilizer.

Although the compatibilizer may be reactively extruded with the TPU before contact with the other engineering thermoplastic and the polyolefin, it is not necessary to do so. The compatibilizer, the second engineering thermoplastic, the polymeric hydrocarbon, and the TPU can be conveniently blended together and reactively extruded at depolymerization temperatures, preferably not less than 180° C, and more preferably not less than 200° C; and preferably not greater than 300° C, and more preferably not greater than 250° C.

The compatibilized blends of the present invention generally exhibit improved properties such as paintability, tensile strength, dart impact and weldline strength as compared to blends that are not compatibilized. These blends are useful in the production of parts for motor-vehicles such as bumpers, spoilers, fenders, as well as tools, appliances, sporting goods, and tube connectors.

The following examples are for illustrative purposes only and are not intended to limit the scope of this invention.

Example 1 – Compatibilization of Polypropylene and a Polyurethane Engineering Thermoplastic Resin

A. Preparation of the Compatibilizer

A compatibilizer for the polypropylene and polyurethane engineering thermoplastic resin was prepared by tumble blending EPOLENE™ PP 3003 wax (polypropylene grafted with from about 0.5 to about 1 weight percent maleic anhydride) with 2-aminoethanol (1 weight percent) in a plastic bag. The mixture was then extruded through a 34-mm twin screw extruder maintained at 200 rpm and at 220° C. The residence time was about 20 seconds. Conversion of maleic anhydride to the corresponding imide-alkanol was verified by IR spectroscopy.

B. Preparation of the Compatibilized PP-ISOPLAST Mixture

A portion of the compatibilizer as prepared in step A (5 percent by weight) was tumble mixed with HIDMONT™ PD 701 Polypropylene (a trademark of Hidmont, 65 weight percent), and dried XUS 72301.00L engineering thermoplastic polyurethane (30 weight percent), which was prepared substantially as described in U.S. Patent 5,627,254 by reactive extrusion of 4,4'-diisocyanatodiphenylmethane (68 weight percent), triethylene glycol (16.2 weight percent), 1,4-butanediol (14.6 weight %), tris-nonylphenyl phosphite (0.13 weight percent), FOMREZ™ UL-22 catalyst (trademark of Witco Corporation, 0.06 weight percent), ADVAWAX™ 280 (a trademark of Morton Industries, 0.25 weight percent), IRGANOX™ 1010 stabilizer (trademark of

Ciba-Geigy, 0.25 weight percent), and UVTEX™ OB 328 stabilizer (a trademark of Ciba Geigy 0.002 weight percent). The mixture was then compounded in the twin screw extruder at 220° C. The resultant blend was dried in a desiccant drier for 4 hours then cut into 6" x 0.5" x 0.125" (15-
5 cm x 1.3-cm x 0.3-cm) test specimens and molded at 220° C. The weldline strength (tensile strength from butweldline) was 4200 psi. The elongation to break was found to be 420%.

Example 2 – Compatibilization of Polyethylene Terephthalate and an Ethylene-Octene Copolymer

High Density Polyethylene grafted with about 0.8 to about 1 weight percent maleic anhydride was compounded with 2-aminoethanol (1 weight percent) on the twin screw extruder at 220° C to form a compatibilizer precursor. A portion of this precursor (5 weight percent), was
10 tumble mixed with TRAYTUF™ 5900 PET (a trademark of Shell Chemical, 70 weight percent), AFFINITY™ 8180 ethylene-octene copolymer (a trademark of The Dow Chemical Company, 20 weight percent), and XUS 72301.00L engineering thermoplastic polyurethane (5 weight percent). The blend was compounded on the twin screw extruder as before. Test specimens were cut and molded as described in Example 1. The unnotched IZOD impact at weldline was found to be 6.5
15 ft-lb/in.

Example 3 – Compatibilization of Polyethylene Terephthalate and High Density Polyethylene

The compatibilizer precursor as prepared in Example 2 (5 weight percent) was tumble mixed with TRAYTUF™ 5900 PET (70 weight percent), LUPOLEN™ L426 1AQ 404 high density polyethylene (a trademark of The Dow Chemical Company, 20 weight percent), and XUS
20 72301.00L engineering thermoplastic polyurethane (5 weight percent). The blend was compounded on the twin screw extruder as before. The unnotched IZOD impact at weldline was found to be 10.8 ft-lb/in.

Example 4 – Compatibilization of Polypropylene with a Thermoplastic Polyurethane Elastomer


- A compatibilizer for the polypropylene and a thermoplastic polyurethane elastomer was prepared by tumble blending EPOLENE™ PP 3003 wax with JEFFAMINE™ M-2005 polyether monoamine (a trademark of Huntsman Petrochemical Corp., 1 weight percent) in a plastic bag.
- 5 The mixture was then extruded through a 34-mm twin screw extruder maintained at 200 rpm and at 220° C. The residence time was about 20 seconds. Conversion of maleic anhydride to the corresponding imide-oxyalkylene was verified by IR spectroscopy. A portion of this compatibilizer was combined with HIDMONT™ PP 701 polypropylene (a trademark of Hidmont Corp., 75 weight percent) and VORANOL™ based TPU XU 63142 (a trademark of The Dow
- 10 Chemical Company, 20 weight percent). Dart impact at 25° C was found to be 445 in-lbs. At 15° C, dart impact was 358 in-lbs. At 0° C, dart impact was 338 in-lbs. The tensile strength was 3900 psi.

Example 5 – Compatibilization of Ethylene-Octene Copolymer with a Thermoplastic Polyurethane

- A 50:50 weight percent mixture of FUSABOND™ MN-493D resin (a trademark of du Pont de Nemours, 0.5 weight percent grafted ethylene-1-octene copolymer) and AFFINITY™ ethylene-1-octene copolymer (a trademark of The Dow Chemical Company) were compounded and added along with ethylene diamine (0.25% by weight) to a 34-mm twin screw extruder maintained at 200 rpm and 220° C. The residence time was 20 seconds. The ethylene diamine was introduced through as side injection during compounding. Conversion of the maleic
- 15 anhydride to the corresponding imide was verified by IR spectroscopy. This diluted compatibilizer (4% by weight) was combined with ISOPLAST XUS 72301 engineering thermoplastic polyurethane (88 weight percent) and AFFINITY 8180 ethylene-1-octene copolymer. The unnotched Izod impact value of this composition after molding was 41 ft-lb/in²
- 20

CLAIMS:


1. A composition comprising a blend or reactive product of a) a thermoplastic polyurethane, and b) a compatibilizer, which is a first polymeric hydrocarbon that contains isocyanate-reactive groups or polyoxyalkylene groups.
- 5 2. The composition of Claim 1 wherein the first polymeric hydrocarbon is selected from the group consisting of polypropylene, high density polyethylene, low density polyethylene, linear low density polyethylene, substantially linear ethylene/ α -olefin copolymers, polystyrene, poly- α -methylstyrene, polyvinyltoluene, and ethylene-styrene interpolymer wherein the compatibilizer contains pendant isocyanate-reactive groups having the following structure:
- 10



- where X is NH or O; R₁ is H or C₁-C₄ alkyl; each R is independently H, -CH₃, or -CH₂CH₃; and where x is from 0 to 50, wherein the concentration of the pendant groups is not less than 0.1 weight percent, and not more than 2 weight percent, based on the weight of the compatibilizer.
- 15

3. The composition of Claim 2 wherein the thermoplastic polyurethane is an engineering thermoplastic polyurethane having a T_g of greater than 50° C, the first polymeric hydrocarbon is polypropylene or an ethylene-1-octene copolymer, x is 0, and R₁ are R are each H.
- 20 4. The composition of Claim 2 wherein the thermoplastic polyurethane is a soft thermoplastic polyurethane having a T_g of less than 25° C, R₁ is methyl and R is H.
5. The composition of any of Claims 1-4 which further includes a second polymeric hydrocarbon selected from the group consisting of polypropylene, high density polyethylene, low density polyethylene, linear low density polyethylene, substantially linear ethylene/ α -olefin copolymers, polystyrene, poly- α -methylstyrene,
- 25 polyvinyltoluene, and ethylene-styrene interpolymer.

6. A composition comprising a blend or reactive mixture of a) a thermoplastic polyurethane, and b) a compatibilizer, which is a first polymeric hydrocarbon that contains isocyanate reactive groups or polyoxyalkylene groups, and c) a second polymeric hydrocarbon, wherein the first and second polymeric hydrocarbons are each independently selected from the group consisting of polypropylene, high density polyethylene, low density polyethylene, linear low density polyethylene, substantially linear ethylene/ α -olefin copolymers, polystyrene, poly- α -methylstyrene, polyvinyltoluene, and ethylene-styrene interpolymer.
7. The composition of Claim 6 wherein the thermoplastic polyurethane is an engineering thermoplastic polyurethane having a T_g of greater than 50° C, the second polymeric hydrocarbon is polypropylene, ethylene-1-octene copolymer, or high density polyethylene, and the compatibilizer is polypropylene, ethylene-1-octene copolymer, or high density polyethylene containing pendant isocyanate reactive groups having the following structure:




15

where X is NH or O, and wherein the concentration of the pendant groups is not less than 0.1 weight percent, and not more than 2 weight percent, based on the weight of the compatibilizer, with the proviso that when the second polymeric hydrocarbon is polypropylene, the compatibilizer contains polypropylene.

8. The composition of either of Claims 6 or 7 which further includes a second engineering thermoplastic selected from the group consisting of polyester, polycarbonate, polyamide, polyoxymethylene, polysulfone, polyarylate, polyarylene oxide, polyvinyl alcohol, polyvinyl acetate, ethylene-vinyl acetate copolymer, ethylene-vinyl alcohol copolymer, and polyether lactone, and wherein the thermoplastic polyurethane is an engineering thermoplastic polyurethane having a T_g of more than 50° C.
9. A method of preparing a compatibilizing composition comprising the step of compounding under reactive conditions a) a thermoplastic polyurethane, and b) a compatibilizer, which is a first polymeric hydrocarbon that contains isocyanate

reactive groups wherein the compatibilizer contains pendant isocyanate-reactive groups having the following structure:



where X is NH or O, each R is independently H, -CH₃, or -CH₂CH₃; and where x is from 0 to 50, wherein the concentration of the pendant groups is not less than 0.1 weight percent, and not more than 2 weight percent, based on the weight of the compatibilizer.

10. The method of Claim 10 wherein the thermoplastic polyurethane is an engineering thermoplastic polyurethane having a T_g of greater than 50° C, wherein x is 0, and R is H, which method further includes the step of compounding a second polymeric hydrocarbon along with the thermoplastic polyurethane and the compatibilizer, where the concentration of the thermoplastic polyurethane added to the blend is from 1 to 10 weight percent, based on the weight of the compatibilizer, the thermoplastic polyurethane, the second polymeric hydrocarbon, and the second engineering thermoplastic; and where the concentration of the compatibilizer added to the blend is from 1 to 10 percent, based on the weight of the compatibilizer, the thermoplastic polyurethane, the second polymeric hydrocarbon, and the second engineering thermoplastic.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/31279

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08L75/04 C08L23/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

CHEM ABS Data, EPO-Internal, PAJ, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 837 097 A (ADVANCED ELASTOMER SYSTEMS) 22 April 1998 (1998-04-22)	1-3,5-7, 9,10
Y	page 3, line 1 -page 5, line 58; examples examples 1-9,14-17; tables I-VII	1-10
X	STUTZ, HERBERT ET AL: "Chemical reactions during reactive blending of polyurethanes. Fiction or reality?" MACROMOL. SYMP. (1996), 112(FIFTH EUROPEAN SYMPOSIUM ON POLYMER BLENDS, 1996), 151-158, 1996, XP000984844 the whole document	1
X,P	WO 00 63293 A (DUPONT DOW ELASTOMERS LLC) 26 October 2000 (2000-10-26) page 14, line 1 -page 17, line 27; examples	1,5,6
	-/--	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

12 March 2001

Date of mailing of the international search report

05/04/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

Hutton, D

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/31279

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 347 794 A (DOW CHEMICAL CO) 27 December 1989 (1989-12-27) page 3, line 22 -page 7, line 8; examples ----	1,5,6
X	US 4 423 185 A (MATSUMOTO KOICHI ET AL) 27 December 1983 (1983-12-27) abstract; examples 1-3,8 ----	1
X	GB 1 440 030 A (BASF AG) 23 June 1976 (1976-06-23) page 1, line 36 -page 2, line 62; examples 1,3 ----	1,5,6
X	EP 0 353 673 A (GOODRICH CO B F) 7 February 1990 (1990-02-07) page 3, line 1 -page 4, line 41; examples ----	1
Y	US 5 668 217 A (CLARK RICHARD JAMES) 16 September 1997 (1997-09-16) column 2, line 18 -column 9, line 4; claims; examples ----	1-10
Y	WO 93 02113 A (EXXON CHEMICAL PATENTS INC) 4 February 1993 (1993-02-04) page 1, paragraph 1 -page 2, paragraph 2 page 5, paragraph 3 -page 16, paragraph 2 page 17, paragraph 2; claims 1-18; examples ----	1-10
A	EP 0 732 349 A (BAYER AG) 18 September 1996 (1996-09-18) page 2, line 25 -page 4, line 40; examples -----	1,5,6

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/31279

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0837097	A	22-04-1998	DE 69603734 D	16-09-1999
			DE 69603734 T	27-04-2000
			ES 2136927 T	01-12-1999
			JP 10130362 A	19-05-1998
			US 5852118 A	22-12-1998
WO 0063293	A	26-10-2000	AU 4237000 A	02-11-2000
EP 0347794	A	27-12-1989	US 4883837 A	28-11-1989
			AU 607077 B	21-02-1991
			AU 3679789 A	04-01-1990
			CA 1332481 A	11-10-1994
			DE 68917041 D	01-09-1994
			DE 68917041 T	02-03-1995
			ES 2057023 T	16-10-1994
			JP 2255846 A	16-10-1990
			JP 2711144 B	10-02-1998
US 4423185	A	27-12-1983	NONE	
GB 1440030	A	23-06-1976	DE 2245957 A	28-03-1974
			BE 804931 A	18-03-1974
			FR 2200321 A	19-04-1974
			IT 998591 B	20-02-1976
			NL 7312388 A	21-03-1974
EP 0353673	A	07-02-1990	US 4975207 A	04-12-1990
			AT 95826 T	15-10-1993
			AU 3913489 A	01-02-1990
			BR 8903867 A	20-03-1990
			CA 1338912 A	11-02-1997
			DE 68909862 D	18-11-1993
			DE 68909862 T	24-02-1994
			ES 2060706 T	01-12-1994
			JP 2160868 A	20-06-1990
			KR 144361 B	15-07-1998
			MX 164163 B	21-07-1992
			US 5149739 A	22-09-1992
US 5668217	A	16-09-1997	DE 69701015 D	03-02-2000
			DE 69701015 T	25-05-2000
			EP 0807662 A	19-11-1997
			ES 2140929 T	01-03-2000
WO 9302113	A	04-02-1993	NONE	
EP 0732349	A	18-09-1996	CA 2168938 A	14-09-1996